

armastone

Naturally Timeless

ANTISTAIN TEST SHEET FOR ARMATILE SAMPLES

MATERIAL Errigal Split Face Sand Stone

PRODUCT FILA:

UNTREATED

FILAMP90ECOPLUS = antistain sealer natural effect – water based

FILAPT10 = anti stain sealer wetting effect – water based


FILAFoB = antistain sealer natural effect – solvent based

FILASTONEPLUS = antistain sealer colour enhancing effect – solvent based

FILAWET = anti stain sealer wetting effect – solvent based



STAIN-PROOFING ACTION



TYPE OF SUBSTANCE	HOURS	UNTREATED	FILAMP90 ECOPLUS	FILAPT10	FILA FoB	FILA STONEPLUS	FILA WET	LEGEND Assessment carried out after 1 HOUR and 6 HOURS of contact with COFFEE and OIL 1. Evident Expanded Stain 2. Evident Stain 3. Stain 4. Light Mark 5. No Alteration
COFFEE	4	1	3	5	4	4	5	
OIL	4	1	5	5	5	5	5	

ENHANCING EFFECT

FILAMP90 ECOPLUS	FILA FoB	FILAPT10	FILA STONEPLUS	FILA WET	The enhancing effect has measured for comparison by visual method with the untreated surface: +0 = no alteration +1 = light enhancing effect +2 = enhancing effect
0	0	1	2	2	